

Test report no.: <i>Testrapport nr.:</i>	89218579.02br	Order No.: <i>Opdracht nr.:</i>	218579	Page 1 of 14 <i>Pagina 1 van 14</i>
Client Reference No.: <i>Klantreferentie nr.:</i>	N/A	Order date: <i>Opdrachtdatum:</i>	12.03.2021	
Client: <i>Klant:</i>	Unifloor Underlay Systems, Arnsbergstraat 4, 7418 EZ Deventer, The Netherlands			
Test item: <i>Testvoorwerp:</i>	Underlayment			
Identification/ Type No.: <i>Benaming / Type nr.:</i>	Jumpax Classic			
Order content: <i>Inhoud opdracht:</i>	Classification of burning behaviour			
Test specification: <i>Testomschrijving:</i>	EN 13501-1:2007+ A1:2009 Classification of burning behaviour Test methods: Ignitability of products subjected to direct impingement of flame (EN ISO 11925-2:2010/C1:2011) and determination of the burning behaviour using a radiant heat source (EN ISO 9239-1:2010)			
Date of sample receipt: <i>Ontvangstdatum monster:</i>	18.03.2021			
Test sample No.: <i>Testproefstuk nr.:</i>	MT21-218579.02			
Testing period: <i>Testperiode:</i>	18.03.2021 - 30.03.2021			
Place of testing: <i>Testlocatie:</i>	Westervoortsedijk 73, 6827 AV Arnhem			
Testing laboratory: <i>Testlaboratorium:</i>	TÜV Rheinland Nederland B.V.			
Test result*: <i>Testresultaat*:</i>	See Other			
tested by: <i>getest door:</i>	 _____ <small>Ordeleider door: M. H. van de Vekker</small>	authorized by: <i>geautoriseerd door:</i>	 _____ <small>Ordeleider door: J. de Wiff</small>	
Date: 16.04.2021 <i>Datum:</i>		Issue Date: 16.04.2021 <i>Datum uitgave:</i>		
Position / functie:	jr. Engineer	Position / functie:	Expert	
Others / <i>Andere:</i>	Test result: See clause 4 on page 5.			
Condition of the test item at delivery: <i>Toestand van het test voorwerp bij ontvangst:</i>	Test item complete and undamaged			
* Legend:	P(ass) = passed a.m. test specification(s)	F(ail) = failed a.m. test specification(s)	N/A = not applicable	N/T = not tested
* Legenda:	P(ass) = voldoet aan test omschrijving	F(ail) = voldoet niet aan test omschrijving	N/A = niet van toepassing	N/T = niet getest
<p>This test report only relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any test mark.</p> <p><i>Dit testrapport heeft alleen betrekking op het voorgenoemde test voorwerp. Zonder toestemming van het testcentrum mag dit testrapport niet in delen worden vermenigvuldigd. Dit keuringsrapport geeft geen recht op het dragen van enig keurmerk.</i></p>				

Test report no.: 89218579.02br
Testrapport nr.:

Page 2 of 12
Pagina 2 van 12

Remarks
Opmerkingen

1	<p>The equipment used during the specified testing period was calibrated according to our test laboratory calibration program. The equipment fulfils the requirements included in the relevant standards. The traceability of the test equipment used is ensured by compliance with the regulations of our management system. Detailed information regarding test conditions, equipment and measurement uncertainty is available in the test laboratory and could be provided on request. For the influence of the measuring uncertainties on the results, reference is made to the validation of the respective methods.</p> <p><i>De apparatuur welke tijdens de gespecificeerde testperiode is gebruikt, is gekalibreerd volgens ons kalibratieprogramma. De apparatuur voldoet aan de eisen welke zijn opgenomen in de relevante normen. De traceerbaarheid van de gebruikte testapparatuurs is gewaarborgd door naleving van de voorschriften in ons kwaliteitsmanagementsysteem. Gedetailleerde informatie over testomstandigheden, apparatuur en meetonzekerheid is beschikbaar in het testlaboratorium en kan op verzoek worden verstrekt. Voor de invloed van de meetonzekerheden op de resultaten wordt verwezen naar de validatie van de respectievelijke methode c.q. verrichting</i></p>
2	<p>As contractually agreed, this document has been signed digitally only. TÜV Rheinland has not verified and unable to verify which legal or other pertaining requirements are applicable for this document. Such verification is within the responsibility of the user of this document. Upon request by its client, TÜV Rheinland can confirm the validity of the digital signature by a separate document. Such request shall be addressed to our Sales department. An environmental fee for such additional service will be charged.</p> <p><i>Zoals contractueel overeengekomen is dit document enkel digitaal ondertekend. TÜV Rheinland heeft niet geverifieerd en kan niet verifiëren welke wettelijke of andere vereisten van toepassing zijn op dit document. Een dergelijke verificatie valt onder de verantwoordelijkheid van de gebruiker van het document. Op verzoek van de opdrachtgever kan TÜV Rheinland de geldigheid van de digitale handtekening bevestigen door een apart document. Een dergelijk verzoek moet worden gericht aan onze verkoopafdeling. Voor een dergelijke extra service zal een milieutoeslag in rekening worden gebracht.</i></p>
3	<p>Test clauses with remark of * are subcontracted to qualified subcontractors and described under the respective test clause in the report. Tests clauses marked with ^a are performed under ISO 17025 accreditation. Deviations of testing specification(s), test locations or customer requirements are listed in specific test clause in the report. This report is only to be read as a whole. No opinions or interpretation are included in this report. This test report consists of multiple pages and is only to be read as a whole. The number of pages can be seen in the header on the top right of each page, the report ends when the last page is reached. TÜV Rheinland Nederland B.V. is solely responsible for the content.</p> <p><i>Test onderdelen welke met * zijn gemarkeerd zijn uitbesteed aan gekwalificeerde onderaannemers en zijn beschreven in het respectievelijke test onderdeel van dit rapport. Test onderdelen welke met ^a zijn gemarkeerd zijn onder ISO 17025 accreditatie uitgevoerd. Afwijkingen van testspecificatie(s), testlocaties of klant eisen zijn vermeld in het van toepassing zijnde onderdeel in het rapport. Het rapport dient als geheel te worden gelezen. Er zijn geen opinies en interpretaties opgenomen binnen het rapport. Dit rapport bestaat uit meerdere pagina's en dient al geheel gelezen te worden. Het aantal pagina's is rechtsboven in de koptekst van dit rapport vermeld en eindigt wanneer de laatste pagina is bereikt. TÜV Rheinland Nederland is als enige verantwoordelijk voor de inhoud van het rapport.</i></p>
4	<p>All rights reserved. No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V.</p> <p>In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties. © 2010 TÜV Rheinland Nederland.</p> <p><i>Alle rechten voorbehouden. Niets uit dit rapport mag worden veelevoudigd, aan derden ter beschikking gesteld en/of door derden onderzocht en/of openbaar gemaakt door middel van druk, fotokopie, microfilm, in elektronische vorm of op welke andere wijze dan ook, zonder uitdrukkelijke voorafgaande schriftelijke toestemming van TÜV Rheinland Nederland B.V.</i></p> <p><i>Indien dit rapport is opgesteld in het kader van een opdracht aan TÜV Rheinland Nederland B.V., zijn de rechten en verplichtingen van contractpartijen onderworpen aan de Algemene Voorwaarden voor Advies-, Onderzoeks- en Certificeringsopdrachten aan TÜV Rheinland Nederland B.V. en/of de betreffende overeenkomst tussen de contractpartijen. © 2010 TÜV Rheinland Nederland</i></p>

Test report no.: 89218579.02br
Testrapport nr.:

Page 3 of 12
Pagina 3 van 12

Product description
Product omschrijving

1	Product details: <i>Product details:</i>	Product name: Jumpax Classic Test item: Underlayment: 3 mm MDF + 4 mm MDF
2	Other: <i>Andere:</i>	Test sample(s), as well sample information, description, product details and intended usage was provided by customer.
3	Test sample obtaining: <i>Selectie van het proefstuk:</i>	<input checked="" type="checkbox"/> Sending by customer <input type="checkbox"/> Sampling by TÜV Rheinland Group <input type="checkbox"/> others:

Figure 1: Picture of the received sample (surface)




Figure 2: Picture of the received sample (back)



Test report no.: 89218579.02br
 Testrapport nr.:

Clause Deel	Requirements - Tests / Vereisten - Tests	Measuring results – Remarks Meetresultaten – Opmerkingen	Result Resultaat
----------------	---	---	---------------------

1	Construction data (indicative) of the product obtained by the testlaboratory after pre-conditioning 01-4.3-P.02-322-WI01		
	Test condition	23 ± 2°C and 50 ± 4% relative humidity	
	Pre conditioning, duration	≥ 48 h & until constant mass is achieved	
	Total thickness (mm)	9.7	
	Total mass (g/m ²)	5388	
	Density (kg/m ³)	558	
	<i>Note: the determined construction data are used for determination of constant mass, the used testmethod is not in accordance with the determination of construction data according the specification standard. Therefore the testresults should be handled as indicative.</i>		

2	Ignitability of products subjected to direct impingement of flame EN ISO 11925-2:2010/C1:2011			
	Date of testing	30.03.2021		
	Pre-conditioning, climate	23 ± 2°C and 50 ± 4% relative humidity		
	Pre-conditioning, duration	≥ 48 h & until constant mass is achieved		
	Description of substrate	Fibre cement board, thickness 8 ± 2 mm, density 1800 ± 200 kg/m ³ conforming to EN 13238:2010		
	Flame application	Surface		
	Flame application time (s)	15		
	Requirements according EN 13501-1:2007+A1:2009	See clause 5		
	Test result(s)			
	Orientation*	N/A		
	Test sample	1	2	3
	Ignition of the sample	Yes	Yes	Yes
	Flame tip reached 150 mm above the application point	No	No	No
	Duration after application when the flame tip reached the 150 mm above the application point (s)	N/A	N/A	N/A
	Extent of damaged area, length (mm)	41	41	41
	Extent of damaged area, width (mm)	12	12	12
	Material melts	No	No	No
	Shrinks away from flame without being ignited	No	No	No
	After glowing	No	No	No
	Flaming droplets/particles which caused ignition of filter paper	No	No	No
* No length or width direction applicable.				

Test report no.: 89218579.02br
 Testrapport nr.:

Clause Deel	Requirements - Tests / Vereisten - Tests	Measuring results – Remarks Meetresultaten – Opmerkingen	Result Resultaat
----------------	---	---	---------------------

3	Determination of the burning behaviour using a radiant heat source EN ISO 9239-1:2010				
	Date of testing	30.03.2021			
	Pre-conditioning, climate	23 ± 2°C and 50 ± 4% relative humidity			
	Pre-conditioning, duration	≥ 48 h & until constant mass is achieved			
	Description of substrate	Fibre cement board, thickness 8 ± 2 mm, density 1800 ± 200 kg/m ³ conforming to EN 13238:2010			
	Fixing method	None, samples are tested loose laid on the substrate			
	Requirements according EN 13501-1:2007+ A1:2009	See clause 5			
	Test result(s)				
	Test sample	1	2	3	Mean
	Orientation*	N/A	N/A	N/A	N/A
	Flame spread (cm)	56	56	55	56
	CHF / HF-30 (kW/m ²)	3.0	3.0	3.1	3.0
	Maximum light attenuation (%)	9.4	14.2	9.3	11.0
	Smoke production (%.min)	50	98	92	80
* No length or width direction applicable. Observations: Specimen 1, 2, and 3: No flashing is observed. Specimen 1, 2, and 3: Extinguished manually after the end of the test duration.					

4	Classification of burning behaviour EN 13501-1:2007+A1:2009 ^a	
	The product, Jumpax Classic , in relation to its reaction to fire behaviour is classified:	D_{fl}
	The additional classification in relation to smoke production is:	s1
	Reaction to fire classification : D_{fl} – s1	
	Field of application <ul style="list-style-type: none"> - As a floor covering in accordance with the nominal product parameters given on page 3. - On end use substrates of classes A1 and A2-s1,d0 according to EN 13238:2010. - Any way of fixation, glued down or loose laid. 	
Statements <ul style="list-style-type: none"> - This document does not represent type approval or certification of the product. - The test results only relate to the behaviour of the test specimens of the examined product under the -particular conditions of the test in laboratory conditions; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. - The validity of this report will expire directly after alterations or modifications of the examined product (combination)(s) and/or the criteria. 		

Test report no.: 89218579.02br
 Testrapport nr.:

Clause Deel	Requirements - Tests / Vereisten - Tests	Measuring results – Remarks Meetresultaten – Opmerkingen	Result Resultaat
----------------	---	---	---------------------

5	Potential classes of reaction to fire performance for floorings EN 13501-1:2007+A1:2009			
	Class	Test method(s)	Classification criteria	Additional classifications
	A1 _{fi}	EN ISO 1182 ^a and	$\Delta T \leq 30 \text{ }^\circ\text{C}$; and $\Delta m \leq 50 \%$; and $t_f = 0$ (i.e. no sustained flaming)	-
		EN ISO 1716	$PCS \leq 2.0 \text{ MJ/kg}$ ^a and $PCS \leq 2.0 \text{ MJ/m}^2$ ^b and $PCS \leq 1.4 \text{ MJ/m}^2$ ^c and $PCS \leq 2.0 \text{ MJ/kg}$ ^d	-
	A2 _{fi}	EN ISO 1182 ^a or	$\Delta T \leq 50 \text{ }^\circ\text{C}$ and $\Delta m \leq 50 \%$ and $t_f \leq 20 \text{ s}$	-
		EN ISO 1716 and	$PCS \leq 3.0 \text{ MJ/kg}$ ^a and $PCS \leq 4.0 \text{ MJ/m}^2$ ^b and $PCS \leq 4.0 \text{ MJ/m}^2$ ^c and $PCS \leq 3.0 \text{ MJ/kg}$ ^d	-
		EN ISO 9239-1 ^e	$CHF \geq 8.0 \text{ kW/m}^2$	Smoke production ^g
	B _{fi}	EN ISO 9239-1 ^e and	$CHF \geq 8.0 \text{ kW/m}^2$	Smoke production ^g
		EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150 \text{ mm}$ within 20 s	-
	C _{fi}	EN ISO 9239-1 ^e and	$CHF \geq 4.5 \text{ kW/m}^2$	Smoke production ^g
EN ISO 11925-2 ^h : Exposure = 15 s		$F_s \leq 150 \text{ mm}$ within 20 s	-	
D _{fi}	EN ISO 9239-1 ^e and	$CHF \geq 3.0 \text{ kW/m}^2$	Smoke production ^g	
	EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150 \text{ mm}$ within 20 s	-	
E _{fi}	EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150 \text{ mm}$ within 20 s	-	
F _{fi}	EN ISO 11925-2 ^h : Exposure = 15 s	$F_s > 150 \text{ mm}$ within 20 s	-	
^a For homogeneous products and substantial components of non-homogeneous products. ^b For any external non-substantial component of non-homogeneous products. ^c For any internal non-substantial component of non-homogeneous products. ^d For the product as a whole. ^e Test duration = 30 min. ^f Critical flux is defined as the radiant flux at which the flame extinguishes or the radiant flux after a test period of 30 min, whichever is the lower (i.e. the flux corresponding with the furthest extent of spread of flame). ^g s1 = Smoke $\leq 750 \%$ minutes; s2 = not s1. ^h Under conditions of surface flame attack and, if appropriate to the end use application of the product, edge flame attack.				

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
Laboratory : TÜV Rheinland Nederland B.V.
Sponsor : Unifloor 89218579
Date of test : Mar. 30 2021

Specimen description : Jumpax Classic MT21.218579.02
Test name : No direction 1
File name : D:\FRPFILES\21030031.CSV
Test number in series : 3

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX21001.CSV

Thickness (mm) : 9.66
Density (kg/m³) : 558

Test duration : 30 minutes (1800 s)
Substrate used? : Yes
Substrate : Calcium silicate
Fixing method : none
Conditioned? : Yes
Conditioning temp. (°C) : 23
Conditioning RH (%) : 50

Test Results


Time to ignition : 2 minutes 04 seconds (124 s)
Time to flameout : 30 minutes (1800 s)
Extent of burning (mm) : 560
Critical flux at extinguishment (kW/m²) : 2.99
HF-10 (kW/m²) : 7.36
HF-20 (kW/m²) : 4.33
HF-30 (kW/m²) : 2.99
Flame spread at 10 minutes (mm) : 280
Flame spread at 20 minutes (mm) : 450
Flame spread at 30 minutes (mm) : 560
Peak light attenuation (%) : 9.37
Time to peak light attenuation : 7 minutes 07 seconds (427 s)
Total integrated smoke (%.min) : 50.25

Potential classification : E(f)
Smoke production classification : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : No direction 1
 File name : D:\FRPFILES\21030031.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	230	11.4	2.615	510	1507	3.5	5.211
110	344	10.5	3.600	560	1787	3.0	5.338
160	393	9.7	3.800	610	-	2.6	-
210	481	8.8	4.211	660	-	2.2	-
260	561	7.7	4.342	710	-	1.9	-
310	649	6.8	4.403	760	-	1.7	-
360	860	5.9	5.037	810	-	1.6	-
410	1061	5.0	5.315	860	-	1.3	-
460	1223	4.2	5.093	910	-	1.2	-

Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
Laboratory : TÜV Rheinland Nederland B. V.
Sponsor : Unifloor 89218579
Date of test : Mar. 30 2021

Specimen description : Jumpax classic MT21-218579.02
Test name : No direction #2
File name : D:\FRPFILES\21030032.CSV
Test number in series : 3

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX21001.CSV

Thickness (mm) : 9.66
Density (kg/m³) : 558

Test duration : 30 minutes (1800 s)
Substrate used? : Yes
Substrate : Calcium silicate
Fixing method : none
Conditioned? : Yes
Conditioning temp. (°C) : 23
Conditioning RH (%) : 50


Test Results

Time to ignition : 2 minutes 04 seconds (124 s)
Time to flameout : 30 minutes (1800 s)
Extent of burning (mm) : 560
Critical flux at extinguishment (kW/m²) : 2.99
HF-10 (kW/m²) : 7.36
HF-20 (kW/m²) : 4.16
HF-30 (kW/m²) : 2.99
Flame spread at 10 minutes (mm) : 280
Flame spread at 20 minutes (mm) : 460
Flame spread at 30 minutes (mm) : 560
Peak light attenuation (%) : 14.16
Time to peak light attenuation : 18 minutes 02 seconds (1082 s)
Total integrated smoke (%.min) : 97.81

Potential classification : E(II)
Smoke production classification : s1

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : No direction #2
 File name : D:\FRPFILES\21030032.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	254	11.4	2.888	510	1496	3.5	5.173
110	328	10.5	3.433	560	1791	3.0	5.350
160	410	9.7	3.965	610	-	2.6	-
210	489	8.8	4.281	660	-	2.2	-
260	563	7.7	4.357	710	-	1.9	-
310	723	6.8	4.905	760	-	1.7	-
360	795	5.9	4.656	810	-	1.6	-
410	965	5.0	4.834	860	-	1.3	-
460	1193	4.2	4.968	910	-	1.2	-

Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Report produced with the Fire Testing Technology FRPSuit software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
Laboratory : TÜV Rheinland Nederland B.V.
Sponsor : Unifloor 89218579
Date of test : Mar. 30 2021

Specimen description : Jumpax classic MT21-218579.02
Test name : No direction #3
File name : D:\FRPFILES\21030033.CSV
Test number in series : 3

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX21001.CSV

Thickness (mm) : 9.66
Density (kg/m³) : 558

Test duration : 30 minutes (1800 s)
Substrate used? : Yes
Substrate : Calcium silicate
Fixing method : none
Conditioned? : Yes
Conditioning temp. (°C) : 23
Conditioning RH (%) : 50

Test Results


Time to ignition : 2 minutes 03 seconds (123 s)
Time to flameout : 30 minutes (1800 s)
Extent of burning (mm) : 550
Critical flux at extinguishment (kW/m²) : 3.08
HF-10 (kW/m²) : 7.94
HF-20 (kW/m²) : >= 10.9
HF-30 (kW/m²) : 3.08
Flame spread at 10 minutes (mm) : 250
Flame spread at 20 minutes (mm) : 45
Flame spread at 30 minutes (mm) : 550
Peak light attenuation (%) : 9.28
Time to peak light attenuation : 25 minutes (1500 s)
Total integrated smoke (%.min) : 91.65

Potential classification : **D(f)**
Smoke production classification : **s1**

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : No direction #3
 File name : D:\FRPFILES\21030033.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	283	11.4	3.218	510	1548	3.5	5.353
110	354	10.5	3.705	560	-	3.0	-
160	456	9.7	4.410	610	-	2.6	-
210	538	8.8	4.710	660	-	2.2	-
260	641	7.7	4.961	710	-	1.9	-
310	730	6.8	4.952	760	-	1.7	-
360	940	5.9	5.506	810	-	1.6	-
410	1046	5.0	5.239	860	-	1.3	-
460	1339	4.2	5.576	910	-	1.2	-

Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.