

Return address: P.O. Box 2220, 6802 CE ARNHEM, The Netherlands

Unifloor Underlay Systems  
Att. Mr. F. Vousten  
Arnsbergstraat 4  
7418 EZ DEVENTER  
The Netherlands

TÜV Rheinland Nederland B.V.  
The Netherlands

Postal address:  
P.O. Box 2220  
6802 CE ARNHEM

Parking and delivery:  
Westervoortsedijk 73  
6827 AV ARNHEM

[www.tuv.com/nl](http://www.tuv.com/nl)

T +31 88 888 7888

[Jaring.de.Wolff@nl.tuv.com](mailto:Jaring.de.Wolff@nl.tuv.com)

### Testreport

**Project number:** 89210247  
**Report number:** 89210247.11br

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Phone number client**  
+31 (0) 570 85 55 33

**Fax number client**  
+31 (0) 570 85 55 44

#### **Received:**

A floor covering combination (underlay system, glue and floorcovering), marked as:  
**“Jumpax Heat Isolator, Jumpax Basic (MDF) with 6 mm Heatblok”;**  
TÜV-reference: MT16-117021.26

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

#### **Sampling procedure:**

The samples are selected by the applicant. The test house has had no influence on the sampling procedure.

The samples have been received on 15/12/2016.

#### **Order:**

Classification of burning behaviour according to EN 13501-1:2007+ A1:2009.

**Appendix**  
I : Flooring Radiant Panel Single  
Specimen Report – 6 pages

Test methods: Ignitability of products subjected to direct impingement of flame (ISO 11925-2:2010/C1:2011) and determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

#### **Results:**

See page three and four.

#### **Appendix:**

See page five up to and including ten.

TRN applies General Terms & Conditions which are filed at the office of the Clerk for civil affairs at the Court in Zutphen (the Netherlands) under number 35/2010, dated November 17th 2010.

## PRODUCT IDENTIFICATION

Applicant : Unifloor Underlay Systems  
Name : Jumpax Heat Isolator, Jumpax Basic (MDF)  
with 6 mm Heatblok \*  
Tested in combination with : 2 mm LVT\*  
Production direction : No production direction applicable\*  
Total thickness (mm) : 16.1\*\*  
Total mass (gr/m<sup>2</sup>) : 9525\*\*  
Density (kg/m<sup>3</sup>) : 593\*\*

\* Applicant's declaration

\*\* Determination by the test house after conditioning to constant mass is achieved.

Date  
03/02/2017

Project number  
89210247

Report number  
89210247.11br

Article  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

Page  
2/10



Figure 1. Picture of the received sample

Date  
03/02/2017

Project number  
89210247

Report number  
89210247.11br

Article  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

Page  
3/10

## TEST RESULTS

### *Ignitability of products subjected to direct impingement of flame* Method EN ISO 11925-2 :2010/C1:2011

Date of testing : 03/01/2017  
 Conditioning time, climate :  $\geq 7$  days,  $23 \pm 2$  °C and  $50 \pm 5$  %  
 Description of substrate : Fibre cement board,  $8 \pm 2$  mm,  $1800 \pm 200$  kg/m<sup>3</sup>  
 conforming to EN 13238.  
 Flame application : Surface.  
 Flame application time : 15 seconds.

| Orientation:                        |     |     |     |
|-------------------------------------|-----|-----|-----|
| Total burning time <sup>1</sup>     | 15  | 15  | 15  |
| Flame tip reaches 150 mm (s)        | No  | No  | No  |
| Extent of damaged area, length (mm) | 35  | 35  | 35  |
| Extent of damaged area, width (mm)  | 12  | 13  | 13  |
| Material melts (yes/no)             | Yes | Yes | Yes |
| Shrinks away <sup>2</sup> (yes/no)  | No  | No  | No  |
| Glowing <sup>3</sup> (sec)          | No  | No  | No  |
| Flaming debris (yes/no)             | No  | No  | No  |
| Ignition of filter paper (yes/no)   | No  | No  | No  |

1 Inclusive a flame application time of 15 or 30 seconds with surface or edge impingement

2 Shrinks away from flame without being ignited

3 The time at which it occurs and its duration

### *Determination of the burning behaviour using a radiant heat source* Method EN ISO 9239-1:2010

Date of testing : 06/01/2017  
 Conditioning time, climate :  $\geq 7$  days,  $23 \pm 2$  °C and  $50 \pm 5$  %  
 Description of substrate : Fibre cement board,  $8 \pm 2$  mm,  $1800 \pm 200$  kg/m<sup>3</sup>  
 conforming to EN 13238.  
 Sampling procedure : By contractor.  
 Description of cleaning used : None.  
 Fixing method : None, sample is tested loose laid on the substrate.

| Test specimen | Flame spread (cm) | CRF (kW/m <sup>2</sup> ) | Peak light attenuation (%) | Smoke production (%.min) |
|---------------|-------------------|--------------------------|----------------------------|--------------------------|
| 1             | 13.0              | 10.3                     | 42.6                       | 104                      |
| 2             | 11.0              | 10.5                     | 45.7                       | 110                      |
| 3             | 12.0              | 10.4                     | 43.3                       | 124                      |
| <b>Mean</b>   | <b>12.0</b>       | <b>10.4</b>              | <b>43.9</b>                | <b>113</b>               |

Note: according the manufacturers declaration there is no production direction applicable, therefore three samples are sufficient for classification.

Specimen 1, 2, and 3: Flashing, transitory- or sustained flaming are observed.

Specimen 1, 2, and 3: Extinguished naturally before the end of the test duration

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

**Page**  
4/10

## CONCLUSION

According to EN 13501-1:2007+ A1:2009 the tested sample of the aforementioned quality “**Jumpax Heat Isolator, Jumpax Basic (MDF) with 6 mm Heatblok**”, in relation to its reaction to fire behaviour is classified: **B<sub>f1</sub>**.

The additional classification in relation to smoke production is: **s1**.

The aforementioned quality meets the requirement of reaction to fire classification:  
**B<sub>f1</sub> – s1**

The classification is valid for the following end use applications:

- End use substrates of classes A1 and A2-s1,d0.
- Any way of fixation, glued down or loose laid.

### Statements:

The test results only relate to the behaviour of the test specimens of the examined product under the particular conditions of the test in laboratory conditions; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. The method might not be suitable if the product is exposed to much larger flames or heat radiant sources.

The validity of this report will expire directly after alterations or modifications of the examined product (combination)(s) and/or the criteria. This report shall not be reproduced, except in full, without the written approval of the testing laboratory.

This document does not represent type approval or certification of the product.

**Author:**  
Mr. M.A. van de Vlekkert



**Review:**  
Mr. J. de Wolff



*All rights reserved.*

*No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V. The results are based upon the samples received and have not to be representative for the total production. TÜV Rheinland Nederland B.V. had no influence on the sampling.*

*In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties.*

© 2010 TÜV Rheinland Nederland B.V.

(End of report)

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

**Page**  
5/10

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 1

### Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010  
Laboratory : TÜV Rheinland Nederland B.V.  
Sponsor : 89210247 Unifloor  
Date of test : Jan. 06 2017

Specimen description : MT16-117021.26 Jumpax Heat Isolator / Jumpax Basic (MDF)  
Test name : # sample 1  
File name : D:\FRPFILES\17010015.CSV  
Test number in series : 3

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX16016.CSV

Thickness (mm) : 16.1  
Density (kg/m<sup>3</sup>) : 593

Test duration : 12 minutes 16 seconds (736 s)  
Substrate used? : Yes  
Substrate : Calcium silicate  
Fixing method : None (loose laid)  
Conditioned? : Yes  
Conditioning temp. (°C) : 23  
Conditioning RH (%) : 50

#### Test Results

Time to ignition : 2 minutes 03 seconds (123 s)  
Time to flameout : 12 minutes 12 seconds (732 s)  
Extent of burning (mm) : 130  
Critical flux at extinguishment (kW/m<sup>2</sup>) : 10.29  
HF-10 (kW/m<sup>2</sup>) : 10.29  
HF-20 (kW/m<sup>2</sup>) : Not calculated (test duration < 20 minutes)  
HF-30 (kW/m<sup>2</sup>) : Not calculated (test duration < 30 minutes)  
Flame spread at 10 minutes (mm) : 130  
Flame spread at 20 minutes (mm) : Not measured  
Flame spread at 30 minutes (mm) : Not measured  
Peak light attenuation (%) : 42.56  
Time to peak light attenuation : 3 minutes 09 seconds (189 s)  
Total integrated smoke (%.min) : 103.77

**Potential classification** : A2(B)/B(B)  
**Smoke production classification** : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRP'Satt software

page 2


**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

**Page**  
6/10



Test name : # sample 1  
File name : D:\FRPFILES\17010015.CSV

### Rake Results

| Position (mm) | Time (s) | Flux (kW/m <sup>2</sup> ) | Qsb (MJ/m <sup>2</sup> ) | Position (mm) | Time (s) | Flux (kW/m <sup>2</sup> ) | Qsb (MJ/m <sup>2</sup> ) |
|---------------|----------|---------------------------|--------------------------|---------------|----------|---------------------------|--------------------------|
| 60            | 198      | 11.1                      | 2.193                    | 530           | -        | 3.7                       | -                        |
| 110           | 258      | 10.5                      | 2.705                    | 560           | -        | 3.1                       | -                        |
| 160           | -        | 10.0                      | -                        | 610           | -        | 2.6                       | -                        |
| 210           | -        | 9.4                       | -                        | 660           | -        | 2.2                       | -                        |
| 260           | -        | 8.4                       | -                        | 710           | -        | 1.9                       | -                        |
| 310           | -        | 7.5                       | -                        | 760           | -        | 1.6                       | -                        |
| 360           | -        | 6.4                       | -                        | 810           | -        | 1.4                       | -                        |
| 410           | -        | 5.3                       | -                        | 860           | -        | 1.2                       | -                        |
| 460           | -        | 4.4                       | -                        | 910           | -        | 1.1                       | -                        |

### Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 1

### Flooring Radiant Panel Single Specimen Report

|                              |  |
|------------------------------|--|
| Standard                     | : EN ISO 9239-1:2010                                 |
| Laboratory                   | : TÜV Rheinland Nederland B.V.                       |
| Sponsor                      | : 89210247 Unifloor                                  |
| Date of test                 | : Jan. 06 2017                                       |
| Specimen description (MDF)   | : MT16-117021.26 Jumpax Heat Isolator / Jumpax Basic |
| Test name                    | : # sample 2   |
| File name                    | : D:\FRPFILES\17010016.CSV                           |
| Test number in series        | : 3  |
| Flux calibration file name   | : C:\FRPSOFT2.9A\CALIB\FLX16016.CSV                  |
| Thickness (mm)               | : 16.1   |
| Density (kg/m <sup>3</sup> ) | : 593  |
| Test duration                | : 14 minutes 10 seconds (850 s)                      |
| Substrate used?              | : Yes  |
| Substrate                    | : Calcium silicate                                   |
| Fixing method                | : None (loose laid)                                  |
| Conditioned?                 | : Yes  |
| Conditioning temp. (°C)      | : 23   |
| Conditioning RH (%)          | : 50   |

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax Basic (MDF) with 6 mm Heatblok

**Page**  
7/10

#### Test Results

|  |   |
|--|---|
| Time to ignition                                     | : 2 minutes (120 s)                           |
| Time to flameout                                     | : 14 minutes 08 seconds (848 s)               |
| Extent of burning (mm)                               | : 110   |
| Critical flux at extinguishment (kW/m <sup>2</sup> ) | : 10.48                                       |
| HF-10 (kW/m <sup>2</sup> )                           | : 10.48                                       |
| HF-20 (kW/m <sup>2</sup> )                           | : Not calculated (test duration < 20 minutes) |
| HF-30 (kW/m <sup>2</sup> )                           | : Not calculated (test duration < 30 minutes) |
| Flame spread at 10 minutes (mm)                      | : 110   |
| Flame spread at 20 minutes (mm)                      | : Not measured                                |
| Flame spread at 30 minutes (mm)                      | : Not measured                                |
| Peak light attenuation (%)                           | : 45.72                                       |
| Time to peak light attenuation                       | : 3 minutes 23 seconds (203 s)                |
| Total integrated smoke (%·min)                       | : 110.02                                      |
| <b>Potential classification</b>                      | : <b>A2(B)/B(I)</b>                           |
| <b>Smoke production classification</b>               | : <b>s1</b>                                   |

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 2


**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

**Page**  
8/10



Test name : # sample 2  
File name : D:\FRPFILES\17010016.CSV

### Rake Results

| Position (mm) | Time (s) | Flux (kW/m <sup>2</sup> ) | Qsb (MJ/m <sup>2</sup> ) | Position (mm) | Time (s) | Flux (kW/m <sup>2</sup> ) | Qsb (MJ/m <sup>2</sup> ) |
|---------------|----------|---------------------------|--------------------------|---------------|----------|---------------------------|--------------------------|
| 60            | 192      | 11.1                      | 2.126                    | 510           | -        | 3.7                       | -                        |
| 110           | 279      | 10.5                      | 2.925                    | 560           | -        | 3.1                       | -                        |
| 160           | -        | 10.0                      | -                        | 610           | -        | 2.6                       | -                        |
| 210           | -        | 9.4                       | -                        | 660           | -        | 2.2                       | -                        |
| 260           | -        | 8.4                       | -                        | 710           | -        | 1.9                       | -                        |
| 310           | -        | 7.5                       | -                        | 760           | -        | 1.6                       | -                        |
| 360           | -        | 6.4                       | -                        | 810           | -        | 1.4                       | -                        |
| 410           | -        | 5.3                       | -                        | 860           | -        | 1.2                       | -                        |
| 460           | -        | 4.4                       | -                        | 910           | -        | 1.1                       | -                        |

### Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use



## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 1

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

**Page**  
9/10

### Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010  
 Laboratory : TÜV Rheinland Nederland B.V.  
 Sponsor : 89210247 Unifloor  
 Date of test : Jan. 06 2017

Specimen description : MT16-117021.26 Jumpax Heat Isolator / Jumpax Basic (MDF)  
 Test name : # sample 3  
 File name : D:\FRPFILES\17010017.CSV  
 Test number in series : 3

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX16016.CSV

Thickness (mm) : 16.1  
 Density (kg/m<sup>3</sup>) : 593

Test duration : 13 minutes 09 seconds (789 s)  
 Substrate used? : Yes  
 Substrate : Calcium silicate  
 Fixing method : None (loose laid)  
 Conditioned? : Yes  
 Conditioning temp. (°C) : 23  
 Conditioning RH (%) : 50

#### Test Results

Time to ignition : 2 minutes 03 seconds (123 s)  
 Time to flameout : 13 minutes 07 seconds (787 s)  
 Extent of burning (mm) : 120  
 Critical flux at extinguishment (kW/m<sup>2</sup>) : 10.39  
 HF-10 (kW/m<sup>2</sup>) : 10.39  
 HF-20 (kW/m<sup>2</sup>) : Not calculated (test duration < 20 minutes)  
 HF-30 (kW/m<sup>2</sup>) : Not calculated (test duration < 30 minutes)  
 Flame spread at 10 minutes (mm) : 120  
 Flame spread at 20 minutes (mm) : Not measured  
 Flame spread at 30 minutes (mm) : Not measured  
 Peak light attenuation (%) : 43.31  
 Time to peak light attenuation : 3 minutes 21 seconds (201 s)  
 Total integrated smoke (%.min) : 124.24

**Potential classification** : A2(f)/B(f)  
**Smoke production classification** : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

**APPENDIX I: Flooring Radiant Panel Single Specimen Report**

Report produced with the Fire Testing Technology FRPSafe software

Page 2


**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.11br

**Article**  
Jumpax Heat Isolator, Jumpax  
Basic (MDF) with 6 mm Heatblok

**Page**  
10/10



Test name : # sample 3  
File name : D:\FRPFILES\17010017.CSV

**Rake Results**

| Position (mm) | Time (s) | Flux (kW/m²) | Qsb (MJ/m²) | Position (mm) | Time (s) | Flux (kW/m²) | Qsb (MJ/m²) |
|---------------|----------|--------------|-------------|---------------|----------|--------------|-------------|
| 60            | 188      | 11.1         | 2.082       | 510           | -        | 3.7          | -           |
| 110           | 344      | 10.5         | 3.606       | 560           | -        | 3.1          | -           |
| 160           | -        | 10.0         | -           | 610           | -        | 2.6          | -           |
| 210           | -        | 9.4          | -           | 660           | -        | 2.2          | -           |
| 260           | -        | 8.4          | -           | 710           | -        | 1.9          | -           |
| 310           | -        | 7.5          | -           | 760           | -        | 1.6          | -           |
| 360           | -        | 6.4          | -           | 810           | -        | 1.4          | -           |
| 410           | -        | 5.3          | -           | 860           | -        | 1.2          | -           |
| 460           | -        | 4.4          | -           | 910           | -        | 1.1          | -           |

Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.